235 Kilvert Street
Warwick, RI 02886

A World-Class Quality Partner
ISO 9001:2008
Registered

PRODUCT: **DRY FLUX**
SILVER BRAZING FLUX

DESCRIPTION:

DRY FLUX is a premium quality brazing flux in powdered form consisting of a unique combination of borates and fluorides for use with torch, induction, furnace, resistance, dip and other heating methods. For convenience in applying, flux may be diluted with water.

TECHNICAL DATA:

Composition	Potassium salts of fluorine and boric acid
Type	Powder
Ph	8.0
Water Content	less than 5%
Application	dip or spray
Containers	3 lb. jars and 25 lb. pails
Specifications	AWS Brazing Flux FB3-F OF499, Type B AMS 3410
Effective Range	1100°F – 1600°F

LIABILITY-DISCLAIMER:

Wolverine Joining Technologies, LLC, seeks to represent reliable information concerning the composition, properties and use of its products. The technical information provided in this publication is provided at no charge and is without guarantee, warranty or responsibility of any kind, expressed or implied.

Wolverine Joining Technologies, LLC
235 Kilvert Street
Warwick, RI 02886
401-739-9550/fax 401-739-9555
www.silvaloy.com