



235 Kilvert Street
Warwick, RI 02886

A World-Class Quality Partner
ISO 9001:2008
Registered

PRODUCT: **SILVALOY[®] 30**
(AWS BAg-2a)

COMPOSITION:

Silver	30.0 wt%
Copper	27.0 wt%
Zinc	23.0 wt%
Cadmium	20.0 wt%
Total Other Elements	0.15 wt% Max

MATERIAL PROPERTIES:

Solidus	1125°F (605°C)
Liquidus	1310°F (710°C)
Brazing Range	1310-1550°F (710-845°C)
Specific Gravity	8.763
Density (toz/cu. in)	4.618
Electrical Conductivity (% IACS)	31
Electrical Resistivity (Michroh-m-cm)	5.5
Color	Light Yellow

DESCRIPTION:

SILVALOY 30 is historically a modification of **SILVALOY[®] 35** with a further reduction in silver content resulting in a higher melting point and a longer melting range (185°F). It is similar to **SILVALOY 35** in performance although it contains less silver. Its broader melting range is helpful where clearances are not uniform. During melting, **SILVALOY 30** passes from the solid state to a mushy or plastic state and progressively to a liquid. If heated slowly through this plastic state (1125-1310°F) the liquid portion may flow from the solid portion. This causes a separation of the alloy into a low temperature melting (fluid) portion and a high temperature melting (solid) portion. This phenomenon is called liquation. The high temperature melting portion will melt only above the normal brazing temperature of **SILVALOY 30**. For this reason, **SILVALOY 30** should be heated rapidly through the melting range.

APPLICATIONS:

Typical applications are the joining of ferrous, nonferrous and dissimilar metals and alloys with close joint clearances. **SILVALOY 30** is mostly used for brazing steel, stainless steel, copper, copper alloys, nickel, nickel alloys or combinations of these metals.



PRODUCT: **SILVALOY[®] 30 - CONTINUED**
(AWS BAg-2a)

SPECIFICATIONS:

AWS A5.8	BAg-2a
ASME	BAg-2a

AVAILABLE FORMS:

Standard forms of **SILVALOY 30** are wire, strip, and preforms.

PROPERTIES OF BRAZED JOINTS:

Generally, the joint strength using **SILVALOY 30** will surpass the strengths of the base metals. Strength is a function of the base metals being joined, type of joint, design of joint, joint clearances and brazing procedures. The recommended maximum operating temperatures for **SILVALOY 30** is up to 400°F in continuous service and up to 600°F in intermittent service. Where improved corrosion resistance is needed, **SILVALOY[®] 50N** and **SILVALOY[®] A40N2** are recommended over silver base filler metals not containing nickel.

SAFETY INFORMATION:

SILVALOY 30 contains cadmium and therefore upon heating may produce toxic fumes. It is essential that adequate ventilation be provided so that personnel will not inhale gases and fumes while brazing. The operation and maintenance of brazing equipment or facility should conform to the provisions of American National Standard (ANSI) Z49.1, "Safety in Welding and Cutting". For more complete information refer to the Material Safety Data Sheet for **SILVALOY 30**.

LIABILITY-DISCLAIMER:

Wolverine Joining Technologies, LLC, seeks to represent reliable information concerning the composition, properties and use of its products. The technical information provided in this publication is provided at no charge and is without guarantee, warranty or responsibility of any kind, expressed or implied.

Wolverine Joining Technologies, LLC
235 Kilvert Street
Warwick, RI 02886
401-739-9550/fax 401-739-9555
www.silvaloy.com